

## Typical Material Properties Style K947S

### TECHNICAL DATA – STYLE K947S

PROPERTY		VALUE	UNIT	TEST METHOD
Basis weight		77	g/m <sup>2</sup>	WSP 130.1
Thickness		0.54	mm	WSP 120.6
Composition	Polyester	51	%	
	Woodpulp	49	%	
Absorbency		485	%	WSP 10.1
Extrinsic absorption capacity		383	ml/m <sup>2</sup>	WSP 10.2
Grab tensile breaking strength (dry)	MD	183	N	ASTM D5034
	XD	83	N	
Strip tensile breaking strength (dry)	MD	223	N	WSP 110.4
	XD	64	N	

[www.sontara.com](http://www.sontara.com)

All properties are typical values based on roll averages. This is not a specification. Please conduct your own tests to ensure consistency for your application. This information is subject to revision as additional knowledge and experience are gained. Jacob Holm & Sontara® make no guarantee of results and assume no obligation or liability whatsoever in connection with this information. No right or license to any intellectual property of Jacob Holm & Sontara® is intended by the publication of these properties. Nominal values corresponding to our current knowledge, for guidance only. MD=lengthwise, XD=crosswise – last update 25/03/2015.

© 2015 Jacob Holm & Sons AG. All rights reserved. Sontara® is a registered trademark of Jacob Holm & Sons AG.