



Manreal, S.A.

M-108, km. 5,6

☒ Apto. Correos 44

28864 Ajalvir (Madrid) España

Tel.: +34 91 884 45 00

Fax: +34 91 884 41 30

e-mail: manreal@manreal.com

http://www.manreal.com

ISO 9001

BUREAU VERITAS
Certification



Product: ALUMINIO (LACADO NITRO) 7 m + ADHESIVO + CELULOSA ANTIGRASA 35 g/m2
ALUMINIUM 7 m (LACQUER) + ADHESIVE + GREASEPROOF PAPER 35 g/m2

Características/Property	Unidad/Unit	V.Nominal / Value	Metodo Ensayo/Method
GRAMAJE TOTAL GRAMMAGE	g/m2	54 +/- 3	ISO R536
RES. TRACCIÓN (L) TENSILE STRENGTH (MD)	KN/m	> 2,3	ISO 1924/1
RES. TRACCIÓN (T) TENSILE STRENGTH (CD)	KN/m	>1,6	ISO 1924/1
ALARGAMIENTO (L) ELONGATION (MD)	%	>1,5	ISO 1924/1
ALARGAMIENTO (T) ELONGATION (CD)	%	> 3	ISO 1924/1
ESTALLIDO BURSTING STRENGTH	Kpa	> 120	ISO 2758
ADHERENCIA ADHESION ALUMINIUM	-	A - B	Manreal

Acondicionamiento de Muestras (UNE 57001):

Test Climate: 50% RH / 23°C

Humedad Relativa 50% +/-2%

Temperatura 23°C +/-1°C

Adherencia **A-B** Conforme: El Aluminio arranca fibra de papel (con celo)

Aluminium Adhesion: Fibre Tearing bond (A-B)

Fecha/Date: 01- 2014

C. Calidad